

Colors hammer effect and cast iron: circa. 0,8 – 1 m²

VOLATILE COMPONENTS CONTENT

VOC = 824 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat. B/5) at the level of 840[g/l] for the ready product.

SUBSTRATE AND SURFACE PREPARATION

Remove loose particles of rust with wire brush. Slightly grind surfaces free of corrosion with abrasive paper. The substrate must be dry, free of dirt and grease. On plastic elements apply primer for plastics. Shake container before use for at least 3 minutes. It is recommended to perform the test spraying. Before operation cover surfaces not to be lacquered. Spray from the distance approximately 25 cm. Use only during dry and windless weather, or in well ventilated rooms, in temperatures between 10 and 25°C.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product components in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Suggest store temperature 10 to 25 °C.

WARRANTY PERIOD

Inter Troton Rust Control-60 months from the production date

All the information is given to the best of our up-to-date knowledge. We take, however, no responsibility for results due to improper usage of our products or unskilful work.

Troton sp.z o.o. Zabrowo